



ARMOROC STRUCTURAL CEMENT BOARD

Published 12/1/15

MULTI SPAN LOADING CONDITION				
(FOR PANELS SPANNING THREE OR MORE SPANS)				
Uniformly Distributed Loads - Lbs per square foot				
Span: Center-to-center of supports (inches)				
ARMOROC PANEL THICKNESS	LOAD GOVERNED BY *	12"	16"	24"
8mm (5/16")	L/360 ▲ limit between supports	37*	15*	4*
	L/240 ▲ limit between supports	53	23*	7*
10mm (3/8")	L/360 ▲ limit between supports	74*	31*	9*
	L/240 ▲ limit between supports	84	46*	13*
12mm (1/2")	L/360 ▲ limit between supports	121	53*	15*
	L/240 ▲ limit between supports	121	68	23*
16mm (5/8")	L/360 ▲ limit between supports	215	121	37*
	L/240 ▲ limit between supports	215	121	53
19mm (3/4")	L/360 ▲ limit between supports	304	171	63*
	L/240 ▲ limit between supports	304	171	76
22mm (7/8")	L/360 ▲ limit between supports	408	229	98*
	L/240 ▲ limit between supports	408	229	102
25mm (1")	L/360 ▲ limit between supports	526	296	131
	L/240 ▲ limit between supports	526	296	131
28mm (1-1/8")	L/360 ▲ limit between supports	660	371	165
	L/240 ▲ limit between supports	660	371	165
32mm (1-1/4")	L/360 ▲ limit between supports	863	485	215
	L/240 ▲ limit between supports	863	485	215
38mm (1-1/2")	L/360 ▲ limit between supports	1217	684	304
	L/240 ▲ limit between supports	1217	684	304

* Values marked with an asterik (*) are governed by the corresponding deflection ratio. All other load values are governed by a bending strength value of 9 N/mm² (1,305 psi) and Modulus of Elasticity in Bending of 3,000 N/mm² as listed in ISO 8335 which is the minimum allowable performance requirement of the ISO 8335 for CBPB. ARMOROC[®] performance against ISO 8335 shall be considered equal or superior.

¹ If ARMOROC[®] panels are allowed to become saturated, reduce live load working capacity by approximately 30% until panels have re-dried. All load data remains valid for re-dried panels.

² A safety factor of 4 was applied during the preparation of the data presented in this table.

³ Weight of panel and flooring must be subtracted from table values to calculate live load capacity.

⁴ Values in this table generated by Progressive Engineering Inc., PEI Project No. 2015-1816

⁵ All ARMOROC[®] installations must be designed and reviewed by a qualified architect or engineer. Panels perpendicular to supports. Minimum 19mm (3/4") thick panels for structural floor applications, maximum span of 24" on center. Must comply with local building code requirements for loading. Refer to installation specifications for additional information.

Ameriform, LLC., 41 Pope Rd., Holliston, MA 01746
Ph: (508)429-1470 www.ameriformllc.com www.armoroc.com

